



ZINSSER® ALLCOAT EXTERIOR MATT

Outdoor paint provides ultimate performance on all surfaces

- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour

ZINSSER® ALLCOAT EXTERIOR MATT

ОПИСАНИЕ

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Matt is not a rust inhibitive product, apply only on previously protected metal.

ПРЕПОРЪЧАНА УПОТРЕБА

Developed for all outside surfaces, ALLCOAT® Exterior Matt is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Matt can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Matt provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Matt works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,25
Гланцово ниво:	Мат
Гланцово ниво при 60°:	± 2%
Гланцово ниво при 85°:	± 3%
Съдържание на твърди частици в тегло:	40%
Съдържание на твърди вещества в обема:	40%
Пропускливост на водни пари:	Sd = 0,44 m (V2 EN ISO 7783)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух за употреба:	1 h
Готов за повторно нанасяне:	1 h
Напълно втвърден:	7 days

МОКЪР СЛОЙ

100 µm/coat

СУХ СЛОЙ

40 µm/coat

РАЗХОДНА НОРМА

8 - 12 m²/l/coat

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m² per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

НАЧИН НА УПОТРЕБА

Mix carefully before use.

УСЛОВИЯ ЗА НАНАСЯНЕ

10°C-32°C, < 85% R.H.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Apply with brush with synthetic bristle

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Apply with synthetic roller

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Nozzle: 0.017 / Pressure: 140 - 170 bar

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use lukewarm soapy water to clean off stains and materials.

ЗАБЕЛЕЖКИ

ALLCOAT® Exterior Matt is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. New or unweathered powder coatings or plastisols must be degreased and carefully sanded prior to application of Allcoat Exterior Matt. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Matt has no anti corrosive properties; apply Zinsser 123 or Noxyde+ (Airless application) on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer or Noxyde+ (Airless application).

ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	35 g/l
Категория ЛОС:	A/d
Ограничение за ЛОС:	130 g/l (2010)
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Дата на издаване: 04/07/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu