





## **ZINSSER® ALLCOAT EXTERIOR MATT**

# **Outdoor paint provides ultimate** performance on all surfaces

- ٠ Excellent colour retention
- ٠ Weather resistant
- ٠ Can be applied to different types of surfaces
- ٠ Flexible coating
- Recoatable in 1 hour

## WWW.ZINSSEREUROPE.EU

## ZINSSER® ALLCOAT EXTERIOR MATT

#### DESCRIPTION

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Matt is not a rust inhibitive product, apply only on previously protected metal.

#### **RECOMMENDED USE**

Developed for all outside surfaces, ALLCOAT® Exterior Matt is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Matt can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Matt provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Matt works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®

#### **TECHNICAL DATA**

Density (g/cm <sup>3</sup> ):	1,25
Gloss Level:	Matt
Gloss level at 60°:	± 2%
Gloss level at 85°:	± 3%
Solids Content in weight:	40%
Solids content in volume:	40%
Water Vapour Permeability:	Sd = 0,44 m (V2 EN ISO 7783)

#### DRY TIMES BY 20° C/RH 50%

Dry to handle: 1 h Drv to recoat: 1 h Fully cured: 7 days

#### **RECOMMENDED WET FILM THICKNESS**

100 µm/coat

### **RECOMMENDED DRY FILM THICKNESS**

40 um/coat

#### THEORETICAL CONSUMPTION

8 - 12 m<sup>2</sup>/l/coat

#### PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m<sup>2</sup> per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

#### SURFACE PREPARATION

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

#### **DIRECTIONS FOR USE**

Mix carefully before use.

#### APPLICATION CONDITIONS

10°C-32°C, < 85% R.H.

#### **APPLICATION & THINNING: BRUSH**

Apply with brush with synthetic bristle

#### **APPLICATION & THINNING: ROLLER**

Apply with synthetic roller

#### **APPLICATION & THINNING: AIRLESS SPRAY**

Nozzle: 0.017 / Pressure: 140 - 170 bar

#### **CLEANING OF EQUIPMENT / SPILLS**

Use lukewarm soapy water to clean off stains and materials.

#### REMARKS

ALLCOAT® Exterior Matt is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. New or unweathered powder coatings or plastisols must be degreased and cafrefully sanded prior to application of Allcoat Exterior Matt. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first, ALLCOAT® Exterior Matt has no anti corrosive properties: apply Zinsser 123 or Noxyde+ (Airless application) on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer or Noxyde+ (Airless application).

#### SAFETY DATA

VOC level VOC category: VOC limit: Remarks regarding safety: 35 a/l A/d 130 g/l (2010) Consult Safety Data Sheet and Safety Information printed on the can.

#### SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 05/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

#### ust-Oleum Netherlands B.V.

Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T : +31 (0) 165 593 636 : +31 (0) 165 593 600 info@rust-oleum.ei

#### Tor Coatings Ltd (Rust-Oleum In Shadon Way, Portobello Ind. Estate Birtley, Chester-le-Street DH3 2RE United Kingdom m Industrial) T : +44 (0)1914 113 146 +44 (0)1914 113 147 info@rust\_oleum eu

ust-Ale m France S.A.S. 38, av. du Gros Chêne 95322 Herblay France T : +33(0) 130 40 00 44 +33(0) 130 40 99 80 info@rust-oleum.eu

#### N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem

Belgium : +32 (0) 13 460 200 +32 (0) 13 460 201 info@rust-oleum.eu