



## ZINSSER® ALLCOAT EXTERIOR MATT

# Outdoor paint provides ultimate performance on all surfaces

- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour



# ZINSSER® ALLCOAT EXTERIOR MATT

## DESCRIPTION

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Matt is not a rust inhibitive product, apply only on previously protected metal.

## ODPORÚČANÉ POUŽITIE

Developed for all outside surfaces, ALLCOAT® Exterior Matt is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Matt can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Matt provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Matt works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®

## TECHNICAL DATA

|                                  |                              |
|----------------------------------|------------------------------|
| Hustota (g/cm <sup>3</sup> ):    | 1,25                         |
| Úroveň lesku:                    | Matt                         |
| Úroveň lesku pri 60°:            | ± 2%                         |
| Úroveň lesku pri 85°:            | ± 3%                         |
| Obsah pevných látok v hmotnosti: | 40%                          |
| Obsah pevných látok v objeme:    | 40%                          |
| Priepustnosť vodnej pary:        | Sd = 0,44 m (V2 EN ISO 7783) |

## DRY TIMES BY 20° C/RH 50%

|                               |        |
|-------------------------------|--------|
| Suché na manipuláciu:         | 1 h    |
| Suchý na opätovné natieranie: | 1 h    |
| Úplne vytvrdnuté:             | 7 days |

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm/coat

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm/coat

## TEORETICKÁ SPOTREBA

8 - 12 m<sup>2</sup>/l/coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m<sup>2</sup> per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

## PRÍPRAVA POVRCHU

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

## NÁVOD NA POUŽITIE

Mix carefully before use.

## PODMIENKY APLIKÁCIE

10°C-32°C, < 85% R.H.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply with brush with synthetic bristle

## APLIKÁCIA A RIEDENIE: VALEC

Apply with synthetic roller

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 0.017 / Pressure: 140 - 170 bar

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Use lukewarm soapy water to clean off stains and materials.

## POZNÁMKY

ALLCOAT® Exterior Matt is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. New or unweathered powder coatings or plastisols must be degreased and carefully sanded prior to application of Allcoat Exterior Matt. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Matt has no anti corrosive properties; apply Zinsser 123 or Noxyde+ (Airless application) on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer or Noxyde+ (Airless application).

## SAFETY DATA

|                         |  |
|-------------------------|--|
| Úroveň VOC:             | 35 g/l   |
| Kategória VOC:          | A/d  |
| Limit VOC:              | 130 g/l (2010)   |
| Poznámky k bezpečnosti: | Consult Safety Data Sheet and Safety Information printed on the can. |

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last\_updated: 05/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu