



## ZINSSER® ALLCOAT EXTERIOR MATT

# Outdoor paint provides ultimate performance on all surfaces

- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour

# ZINSSER® ALLCOAT EXTERIOR MATT

## BESKRIVNING

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Matt is not a rust inhibitive product, apply only on previously protected metal.

## REKOMMENDERAD ANVÄNDNING

Developed for all outside surfaces, ALLCOAT® Exterior Matt is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Matt can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Matt provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Matt works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®

## TEKNISK DATA

|                          |                              |
|--------------------------|------------------------------|
| Densitet:                | 1,25                         |
| Glansnivå:               | Matt                         |
| Glansnivå vid 60°:       | ± 2%                         |
| Glansnivå vid 85°:       | ± 3%                         |
| Torrsubstansvikt:        | 40%                          |
| Torrsubstansvolym:       | 40%                          |
| Kondensgenomsläpplighet: | Sd = 0,44 m (V2 EN ISO 7783) |

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

|                  |        |
|------------------|--------|
| Hanteringstorr:  | 1 h    |
| Övermålningsbar: | 1 h    |
| Fullt härdad:    | 7 days |

## REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm/coat

## REKOMMENDERAD TORRFILMSTJOCKLEK

40 µm/coat

## TEORETISK FÖRBRUKNING

8 - 12 m²/l/coat

## PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m² per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

## YTFÖRBEREDELSE

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

## BRUKSANVISNING

Mix carefully before use.

## APPLICERINGSFÖRHÅLLANDEN

10°C-32°C, < 85% R.H.

## APPLICERING OCH SPÅDNING: PENSEL

Apply with brush with synthetic bristle

## APPLICERING OCH SPÅDNING: ROLLER

Apply with synthetic roller

## APPLICERING OCH SPÅDNING: AIRLESSPRUTA

Nozzle: 0.017 / Pressure: 140 - 170 bar

## RENGÖRING AV UTRUSTNING/SPILL

Use lukewarm soapy water to clean off stains and materials.

## ANMÄRKNINGAR

ALLCOAT® Exterior Matt is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. New or unweathered powder coatings or plastisols must be degreased and carefully sanded prior to application of Allcoat Exterior Matt. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Matt has no anti corrosive properties; apply Zinsser 123 or Noxyde+ (Airless application) on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer or Noxyde+ (Airless application).

## SÄKERHETSDATA

|                           |                                                                      |
|---------------------------|----------------------------------------------------------------------|
| VOC-nivå:                 | 35 g/l                                                               |
| VOC-kategori:             | A/d                                                                  |
| VOC-gräns:                | 130 g/l (2010)                                                       |
| Anmärkningar om säkerhet: | Consult Safety Data Sheet and Safety Information printed on the can. |

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utgivet den: 05/03/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)