



## ZINSSER® ALLCOAT EXTERIOR SATIN

# Outdoor paint for all surfaces



- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour

# ZINSSER® ALLCOAT EXTERIOR SATIN

## BESKRIVELSE

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Satin is not a rust inhibitive product, apply only on previously protected metal.

## ANBEFALET BRUG

Developed for all outside surfaces, ALLCOAT® Exterior Satin is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Satin can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Satin provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Satin works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®.

## TEKNISK DATA

Tæthed:	1,25
Glansgrad:	Satin
Glansgrad ved 60°:	45 - 65%
Tørstofindhold i volumen:	40%
Vanddamppermeabilitet:	Sd = 0,18 m (V2 EN ISO 7783)

## TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Håndteringstør:	1 h
Genbehandlingstør:	1 h
Fuldt hærdet:	7 days

## ANBEFALET VÅDFILMTHYKKELSE

100 µm/coat

## ANBEFALET TØRFILMTHYKKELSE

40µm/coat

## TEORETISK FORBRUG

8 - 12 m<sup>2</sup>/l/coat

## PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m<sup>2</sup> per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

## FORBEHANDLING AF OVERFLADEN

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

## BRUGSANVISNING

Mix carefully before use.

## ANVENDELSESBETINGELSER

> 10°C, < 85% R.H.

## PÅFØRING OG FORTYNDING: PENSEL

Apply with brush with synthetic bristle

## PÅFØRING OG FORTYNDING: RULLE

Apply with synthetic roller

## PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Nozzle: 0.017 / Pressure: 140 - 170 bar

## RENGØRING AF Udstyr/SPILD

Use lukewarm soapy water to clean off stains and materials.

## BEMÆRKNINGER

ALLCOAT® Exterior Satin is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. Before applying ALLCOAT® Exterior Satin, we recommend that you thoroughly sand and degrease unweathered/new powder coatings and similar surfaces. Not suitable for application onto new plastisol or a new powder coating. These surfaces must be fully weathered. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Satin has no anti corrosive properties, so apply Zinsser 123 on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer.

## SIKKERHEDSDATA

VOC-niveau:	80 g/l
VOC-kategori:	A/d
VOC-grænse:	130 g/l (2010)
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 12/01/2024

**Tilgængelige farver og pakningsstørrelser:** Der henvises til den respektive produktside på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

**Ansvarsfraskrivelse:** Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu) eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)