



ZINSSER® ALLCOAT EXTERIOR SATIN

Outdoor paint for all surfaces



- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour

ZINSSER® ALLCOAT EXTERIOR SATIN

BESKRIVELSE

Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Satin is not a rust inhibitive product, apply only on previously protected metal.

ANBEFALT BRUK

Developed for all outside surfaces, ALLCOAT® Exterior Satin is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Satin can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Satin provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.

Two-layer system: The first layer of ALLCOAT® Exterior Satin works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®.

TEKNISKE DATA

Tetthet:	1,25
Glansgrad:	Satinert
Glansgrad ved 60°:	45 - 65%
Tørrestoffinnhold i volum:	40%
Vanndampermeabilitet:	Sd = 0,18 m (V2 EN ISO 7783)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Håndterbar:	1 h
Overmalbar:	1 h
Herdetid:	7 days

ANBEFALT VÅTFILMTYKKELSE

100 µm/coat

ANBEFALT TØRRFILMTYKKELSE

40µm/coat

TEORETISK FORBRUK

8 - 12 m²/l/coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m² per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

KLARGJØRING AV OVERFLATE

The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

BRUKSANVISNING

Mix carefully before use.

PÅFØRINGSBETINGELSER

> 10°C, < 85% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply with brush with synthetic bristle

PÅFØRING & FORTYNNING: RULLE

Apply with synthetic roller

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 0.017 / Pressure: 140 - 170 bar

RENGJØRING AV UTSTYR/SPILL

Use lukewarm soapy water to clean off stains and materials.

MERKNADER

ALLCOAT® Exterior Satin is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. Before applying ALLCOAT® Exterior Satin, we recommend that you thoroughly sand and degrease unweathered/new powder coatings and similar surfaces. Not suitable for application onto new plastisol or a new powder coating. These surfaces must be fully weathered. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Satin has no anti corrosive properties, so apply Zinsser 123 on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer.

SIKKERHETSDATA

VOC nivå:	80 g/l
VOC kategori:	A/d
VOC grense:	130 g/l (2010)
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 12/01/2024

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu