ZINSSER®
QUALITY SINCE 1849

ZINSSER® ALLCOAT EXTERIOR SATIN

Outdoor paint for all surfaces

- Excellent colour retention
- Weather resistant
- Can be applied to different types of surfaces
- Flexible coating
- Recoatable in 1 hour

WWW.ZINSSEREUROPE.EU

ZINSSER® ALLCOAT EXTERIOR SATIN

DESCRIPTION
Developed for the durable decoration of wood, metal, masonry, plastic, concrete and façade cladding. Self-priming, sanding is unnecessary. Protects dry coating against contamination by mould. ALLCOAT® Exterior Satin is not a rust inhibitive product, apply only on previously protected metal.

ODPORÚČANÉ POUŽITIE
Developed for all outside surfaces, ALLCOAT® Exterior Satin is ideal for use on wood, plastic, galvanised metal, steel, façade cladding, weathered bitumen, plaster, brick, stone, concrete, and more. ALLCOAT® Exterior Satin can be used as a primer and adheres directly on existing glossy coatings without the need for sanding. A separate primer is unnecessary for most applications. ALLCOAT® Exterior Satin provides superb resistance to cracking, blistering, flaking, rain, and severe weather conditions.
Two-layer system: The first layer of ALLCOAT® Exterior Satin works as a primer and seals the surface. The top layer completes the sealing process. Where necessary, apply Zinsser B-I-N® to bleeding knots and resin streaks. For new
or unpainted cedar, redwood, or other resinous timbers prime with Zinsser Cover Stain®.

TECHNICAL_DATA

Hustota (g/cm³):	1,25
Úroveň lesku:	Satin
Úroveň lesku pri 60º:	45 - 65%
Obsah pevných látok v objeme:	40%
Priepustnosť vodnej pary:	Sd = 0,18 m (V2 EN ISO 7783)

DRY TIMES BY 20º C/RH 50%

Suché na manipuláciu:	1 h
Suchý na opätovné natieranie:	1 h
Úplne vytvrdnuté:	7 days

ODPORÚČANÁ HRÚBKA MOKRÉHO FILMU
100 µm/coat

ODPORÚČANÁ HRÚBKA SUCHÉHO FILMU
40µm/coat

TEORETICKÁ SPOTREBA
8 - 12 m²/l/coat

PRAKTICKÁ VÝDATNOSŤ
Practical coverage depends on many factors such as porosity and roughness of the substrate. On porous surfaces coverage will be reduced e.g. sawn timber - 4-8 m² per litre. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

PRÍPRAVA POVRCHU
The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using Rust-Oleum ND14. Use Mathys AMW concentrate to remove algae and mould.

NÁVOD NA POUŽITIE
Mix carefully before use.

PODMIENKY APLIKÁCIE
10°C-32°C, < 85% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC
Apply with brush with synthetic bristle

APLIKÁCIA A RIEDENIE: VALEC
Apply with synthetic roller

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE
Nozzle: 0.017 / Pressure: 140 - 170 bar

ČISTENIE ZARIADENIA / POSTRIEKANIE
Use lukewarm soapy water to clean off stains and materials.

POZNÁMKY
ALLCOAT® Exterior Satin is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. New or unweathered powder coatings or plastisols must be degreased and cafrefully sanded prior to application of Allcoat Exterior Satin. Not suitable onto PVDF cladding : apply Rust-Oleum PVDF Primer first. ALLCOAT® Exterior Satin has no anti corrosive properties; apply Zinsser 123 or Noxyde+ (Airless application) on bare ferrous metal surfaces. Onto rusty surfaces, prime with Rust-Oleum® Peganox® or CombiColor® Aqua Primer or Noxyde+ (Airless application).

SAFETY DATA

Úroveň VOC:	80 g/l
Kategória VOC:	A/d
Limit VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 22/06/2026

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu