



ZINSSER® B-I-N AQUA

White pigmented water-based primer-sealer

- Ultra-low odour.
- Contains only trace VOCs (<0.1%).
- Interior and exterior use.
- Effectively primes, seals and blocks stains.
- Locks in problem odours.



ZINSSER® B-I-N AQUA

BESKRIVELSE

B-I-N® Aqua is a high-performance white-pigmented low-odour water-based, knot block primer and sealer that combines fast drying times with unrivalled adhesion and best possible coverage.

ANBEFALET BRUG

Priming: Use as a full-surface primer on wood panels, building boards, doors, frames, PVC, plywood, concrete, glossy paint and varnish, non-ferrous metal such as galvanised metal, copper, aluminium and stainless steel and other paintable surfaces.

Spot-Priming: B-I-N® AQUA is excellent for spot priming knots, resin, stains, etc, and is also ideal for interior spot priming of water stains. Note that the primer on spot-primed areas with a porous surface may show through if the topcoat has poor coverage. This also applies to many ceiling paints and shiny enamels – only use a topcoat with good coverage. For best results bring forward spot primed areas by allowing a minimum of 45 minutes for the spot primed area to dry before overcoating with a full coat of B-I-N® AQUA to the whole area, or to a natural break.

Sealing: B-I-N® AQUA penetrates and seals porous surfaces and dries to a smooth finish with excellent hiding properties. B-I-N® AQUA is an excellent primer for enamel and is ideal for wood, new cured plaster, concrete and concrete block, stucco, drywall, joint compound, uncoated wallcovering and other porous surfaces.

Stain & Odour Blocking: B-I-N® AQUA will effectively block stains from water, nicotine, grease, oil, soot, mildew, tannin, crayon and lipstick. B-I-N® AQUA is also an outstanding odour barrier and effectively blocks all types of odours including fire damage, smoke, nicotine, mildew, pet urine and odour from fireplaces and heaters.

Fire Damage: Replace severely charred substrates and remove loose soot and other contaminants with a dry chemical sponge or duster. Prime damaged surfaces with B-I-N® AQUA to block smoke stains, water stains, and seal odours.

Knots & Sap Streaks: Seal knots and resin with one to two coats of B-I-N® AQUA. If the wood is new, two coats are recommended.

Glossy Surfaces: Glossy enamel paint and clear finishes, cabinets, panelling, glass, Formica®, MDF, ceramic tile and non-ferrous metal can be primed without sanding or deglossing.

TEKNISK DATA

Tæthed:	1,2 - 1,4
Glansgrad:	Mat
Faststofindhold i vægt:	60%
Tørstofindhold i volumen:	50%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringsstør:	25 minutter
Genbehandlingstør:	45 minutter
Fuldt hærdet:	7 dage

ANBEFALET VÅDFILMTYKKELSE

100 – 137 µm

ANBEFALET TØRFILMTYKKELSE

37,5 – 50 µm

TEORETISK FORBRUG

7.5-10 m²/L/coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Surfaces should be clean, dry, sound and free of dust, dirt, excessive chalky material, grime, grease, oil, wax, mildew, wallpaper, adhesive or any contamination that may interfere with adhesion. If unsure, wash surface with an appropriate cleaning solution or solvent and rinse thoroughly. Remove any peeling and/or unsound coatings. Sand any remaining paint film edges smooth. When priming over stained areas, first attempt to remove as much of the stain as possible by washing, sanding, scraping, etc. Allow surface to dry completely before priming.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use. If thinning is required, add no more than 5% water. In most cases only one coat is necessary to prime most surfaces. If excessive absorption occurs over very porous substrates a second coat may be necessary. For best results, prime entire surface before painting.

ANVENDELSESBETINGELSER

Apply when air and surface temperatures are between 7°C and 32°C with a relative humidity of less than 85%.

PÅFØRING OG FORTYNDING: PENSEL

High quality brush. For thinning, do not use more than 5% water.

PÅFØRING OG FORTYNDING: RULLE

3/8" nap roller. For thinning, do not use more than 5% water.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Use a 0.15–0.17" tip at 1700–2200 psi / 120–150 bar. Follow manufacturer's instructions when using spray equipment. Provide adequate ventilation at all times. For thinning, do not use more than 8% water.

RENGØRING AF UDSKYR/SPILD

Clean up spills and paint drips with warm soap and water. Wipe up splatters before they dry. Follow the equipment manufacturer's directions to clean spray equipment.

BEMÆRKNINGER

B-I-N® Aqua can be tinted with up to 25ml of universal tinter per litre. Tinting the primer toward the colour of the topcoat helps it hide in one coat. Apply more on surfaces with odour and stain problems. Paint spot-primed exterior surfaces after they dry. Lower temperatures, higher humidity, and the addition of tint will prolong dry and cure time of the product. For knots and stains, allow 2 hours to dry. When sealing water stains, some stains may appear in the primer as it dries. This is normal. The stain is locked and will not bleed into the topcoat. Not recommended for full surface application on exterior substrates, garage floors, decks, patios, porches, excessively humid interior areas - e.g. sauna rooms, damp surfaces, or surfaces subject to immersion or prolonged contact with water.

Udstedelsesdato: 14/04/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

ZINSSER® B-I-N AQUA

SIKKERHEDSDATA

VOC-niveau:	1 g/l
VOC-færdigblanding:	1 g/l
VOC-kategori:	A/g
VOC-grænse:	30 g/l (2010)
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 32°C.

Udstedelsesdato: 14/04/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu