



ZINSSER® BULLS EYE 1-2-3

Stain blocking sealer & adhesion primer

- Seals stains of graffiti, grease, rust, cedar & redwood tannin
- Rust inhibitive coating, ideal for new metal
- Adheres to most surfaces without pre-sanding or deglossing
- Fast drying
- White and pastel shades

ZINSSER® BULLS EYE 1-2-3

BESKRIVNING

Universal acrylic water based stain blocking sealer and adhesion primer.

REKOMMENDERAD ANVÄNDNING

Product can be applied on interior and exterior walls, ceilings, doors, trim, foundations, railings, and related paintable surfaces. Bulls Eye 1-2-3 adheres on wood, plaster, concrete, gloss enamels, hardboard, glass and tiles. The product provides a rust inhibitive coating on iron railings, steel frames, piping, etc. Resists the growth of mould and mildew on dried film in damp, humid environments. Resistant to high pH surfaces (up to 12,5) including; plaster, poured concrete, concrete block and stucco. Seals porous surfaces and traps most stains in the primer film (graffiti, grease, rust, cedar & redwood tannin, creosote and asphalt stains). Some stains may require a second coat.

Interior Substrates: new or previously painted drywall, cured plaster, cement, poured concrete, concrete block, stucco, wood (pine, fir, birch, oak and plywood), aluminium, iron, steel and galvanized metal, PVC, glossy laminates and other interior surfaces.

Exterior Substrates: recommended for all types of wood (new or previously painted pine, cedar, redwood, plywood and pressure treated wood), hardboard, metal (aluminium, steel, iron and galvanized metal), PVC, fiberglass, masonry (stucco, concrete block, poured concrete and brick).

TEKNISK DATA

Densitet:	1,26
Glansnivå:	Satin
Glansnivå vid 60°:	Satin: 23%
Torrsubstansvikt:	50,5%
Torrsubstansvolym:	34%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	30 minutes
Torktid:	1 h
Fultt hårdad:	7 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

80 - 110 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

30 - 40 µm

ÅTGÅNG

9 - 12 m²/l

ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSER

Surfaces should be clean, dry, sound and free of dust, dirt, excessive chalky material, grime, grease, oil, wax, mildew, wallpaper adhesive or any contamination that may interfere with adhesion. If unsure, always wash surface with a household ammonia and water solution, or an appropriate cleaning solution. Remove any unsoundly adhered coatings. Sand any remaining paint film edges smooth with the surface. Lightly sand exposed exterior wood with 80 to 100 grit sandpaper to remove loose or weathered wood fibres. Attempt to remove existing stains by washing, sanding, scraping, etc.

Kill mildew with a suitable mildew Killer such as Rust-Oleum FK 111.

Remove rust and clean metal and new galvanized substrates with a suitable cleaner such as Rust-Oleum ND14. On wood first spot prime knots with Zinsser® B-I-N Primer-Sealer before priming full surface with Bulls Eye 1-2-3.

APPLICERING

Stir thoroughly before and during application.

APPLICERINGSFÖRHÅLLANDE

Apply when air and surface temperature is between 10 and 32°C and relative humidity is less than 85%. Substrate moisture content should not exceed 12%.

REDSKAP

Use nylon, polyester or synthetic brush. Do not dilute.

APPLICERING OCH SPÄDNING: ROLLER

Use nylon, polyester or synthetic roller. Do not dilute.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Tip size: 0,015 - 0,017 inch. Fluid pressure: 140 - 175 bar. Do not dilute.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Dilute with max 10% water. Atomizing pressure: 2 - 4 bar.

RENGÖRING AV REDSKAP/SPILL

(Warm) water. If dried on tools, let soak overnight in a 1:4 ammonia and water solution.

INFORMATION

Bulls Eye 1-2-3 is not intended for blocking heavy water-stains or for application to floors, decks, roof surfaces or any surface subject to immersion or prolonged contact with water.

Bulls Eye® 1-2-3 can be tinted with [Bulls Eye® 1-2-3 can be tinted with](#) max. 16 ml of universal color paste per liter.

SÄKERHETSDATA

VOC-nivå:	4 g/l
VOC färdigmix:	4 g/l
VOC-kategori:	A/g
VOC-gräns:	30 г/л
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C

Utgivningsdatum: 24/04/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egen syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shandon Way, Portobello Ind. Estate
Birley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu