



ZINSSER® BULLS EYE 1-2-3 PLUS

Water-based primer and sealer

- Primer for every project – inside and outside
- Adheres to most surfaces
- Fixes chalky substrates
- Seals porous substrates
- Seals stains, even water and smoke stains

ZINSSER® BULLS EYE 1-2-3 PLUS

BESKRIVELSE

Universal, cationic epoxy-ester water-based primer and sealer, offering quick drying and excellent sealing properties. For interior and exterior use. Bulls Eye 1-2-3 Plus blocks stains (even water and smoke stains). It adheres to almost all surfaces without prior sanding.

ANBEFALT BRUK

Bulls Eye 1-2-3 Plus can be applied on many interior and exterior surfaces, such like walls, ceilings, doors, trims and other paintable surfaces. Seals porous surfaces.

Traps most stains and bleeding in the primer film: water, graffiti, grease, creosote, asphalt and smoke damage, tannin from oak, walnut, cedar and redwood. If the substrate is very porous or in case of heavy staining, 2 coats may be required before topcoat.

Possible substrate (bare and previously painted):

Drywall, plaster, cement, wood (pine, fir, cedar, redwood, plywood), glass, non-ferrous metal (aluminium, copper, stainless steel, galvanized steel), vinyl, fiberglass, masonry (stucco, concrete, brick), etc.

Not suitable for use on steel or other ferrous metals as flash rusting may occur.

Product contains special resins to bind particles on moderately chalked panelling or painted surfaces.

High pH substrates: can be used on surfaces up to pH 12,5.

Adheres to glossy enamels, wax free varnishes, wood stains, Formica®, PVC and some hard plastics and ceramic tiles without pre-sanding or surface deglossing.

TEKNISKE DATA

Tetthet:	1,4-1,43
Glansgrad:	Satinert
Glansgrad ved 60°:	Satin: 23%
Tørrestoffinnhold i vekt:	55,45%-57,45%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	30 minutes
Overmalbar:	1 h (2h for stains, 24h for tannin, always within the same day for outside use)
Herdetid:	7 days

ANBEFALT VÅTFILMTYKKELSE

80 - 110 µm

ANBEFALT TØRRFILMTYKKELSE

28 - 38 µm

TEORETISK FORBRUK

10 m²/l (do not exceed 7 m²/l to avoid too high film thickness)

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Surfaces should be clean, dry, sound and free of any loose particles and paints, contaminations: grease, oil, wax, mildew and other micro-organism, wallpaper paste etc, bad for adhesion. Always wash surface with appropriate detergent e.g. Mathys Multicleaner. Sand any remaining paint film edges smooth with the surface. Sand exposed exterior wood with 80 to 100 grit sandpaper to remove loose or weathered fibres. Attempt to remove existing stains by washing, sanding, scraping, etc. Spot prime knots and sap streaks with Zinsser® B-I-N Primer before priming full surface with Bulls Eye 1-2-3 Plus.

BRUKSANVISNING

Stir thoroughly before and while using. We only advise spot-priming for topcoats with high opacity. Ground the entire surface for maximum results. Keep the packaging sealed if the product is not used. Do not mix BE 123 Plus with any other paint for incompatibility reasons.

PÅFØRINGSBETINGELSER

Air and surface temperature between 10°C and 25°C and relative humidity of less than 85%. The moisture level of the substrate may not exceed 12%.

PÅFØRING & FORTYNNING: PENSEL

Use a nylon, polyester or synthetic brush. Do not dilute.

PÅFØRING & FORTYNNING: RULLE

Use a nylon, polyester or synthetic roller. Do not dilute.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Spray opening: 0,017 inch..

Pressure: 140 -170 bar.

Do not dilute.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Pressure 3- 4 bar.

RENGJØRING AV UTSTYR/SPILL

Clean with liquid detergent and warm water. Use methylated spirits or appropriate solvent for dried spills or drips. If dried on tools, soak overnight in Mathys Brush Cleaner. Scrub bristles clean with a wire brush. Follow manufacturer's instructions when cleaning spray equipment.

MERKNADER

Bulls Eye 1-2-3 can be tinted towards top coat colour with up to 10ml universal colorant per 1L, improving the covering process by one layer.

Dry time: full bonding guaranteed after primer is totally cured (7 days).

Lower temperatures, high moisture substrate and addition of colorants will extend the dry time and cure time.

Limitations: Not recommended for application to floors or decks or to surfaces subject to immersion or prolonged contact with water. This list of limitations is not exhaustive.

Bulls Eye 1-2-3 Plus is guaranteed to perform as indicated when applied according to label directions to a properly prepared surface. Directions areas complete as possible but cannot encompass all conditions, applications, and / or surfaces beyond manufacturer's control.

Utstedt dato: 04/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produkt databladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produkt datablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

ZINSSER® BULLS EYE 1-2-3 PLUS

SIKKERHETSDATA

VOC nivå:	1.5 g/l
VOC ferdigblandet:	1.5 g/l
VOC kategori:	A/g
VOC grense:	30 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from the production date in a closed can if it is stored in a dry, well ventilated area not exposed to direct sunlight and at temperatures between 5 and 35°C.

Utstedt dato: 04/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu