



ZINSSER® BULLS EYE 1-2-3 PLUS

Water-based primer and sealer

- Primer for every project – inside and outside
- Adheres to most surfaces
- Fixes chalky substrates
- Seals porous substrates
- Seals stains, even water and smoke stains

ZINSSER® BULLS EYE 1-2-3 PLUS

BESKRIVNING

Universal, cationic epoxy-ester water-based primer and sealer, offering quick drying and excellent sealing properties. For interior and exterior use. Bulls Eye 1-2-3 Plus blocks stains (even water and smoke stains). It adheres to almost all surfaces without prior sanding.

REKOMMENDERAD ANVÄNDNING

Bulls Eye 1-2-3 Plus can be applied on many interior and exterior surfaces, such like walls, ceilings, doors, trims and other paintable surfaces. Seals porous surfaces. Traps most stains and bleeding in the primer film: water, graffiti, grease, creosote, asphalt and smoke damage, tannin from oak, wallnut, cedar and redwood. If the substrate is very porous or in case of heavy staining, 2 coats may be required before topcoat. Possible substrate (bare and previously painted): Drywall, plaster, cement, wood (pine, fir, cedar, redwood, plywood), glass, non-ferrous metal (aluminium, copper, stainless steel, galvanized steel), vinyl, fiberglass, masonry (stucco, concrete, brick), etc. Not suitable for use on steel or other ferrous metals as flash rusting may occur. Product contains special resins to bind particles on moderately chalked panelling or painted surfaces. High pH substrates: can be used on surfaces up to pH 12,5. Adheres to glossy enamels, wax free varnishes, wood stains, Formica®, PVC and some hard plastics and ceramic tiles without pre-sanding or surface deglossing.

TEKNISK DATA

Densitet:	1,4-1,43
Glansnivå:	Satin
Glansnivå vid 60°:	Satin: 23%
Torrsubstansvikt:	55,45%-57,45%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	30 minutes
Övermålningsbar:	1 h (2h for stains, 24h for tannin, always within the same day for outside use)
Fullt hårdad:	7 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

80 - 110 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

28 - 38 µm

TEORETISK FÖRBRUKNING

10 m²/l (do not exceed 7 m²/l to avoid too high film thickness)

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Surfaces should be clean, dry, sound and free of any loose particles and paints, contaminations: grease, oil, wax, mildew and other micro-organism, wallpaper paste etc, bad for adhesion. Always wash surface with appropriate detergent e.g. Mathys Multicleaner. Sand any remaining paint film edges smooth with the surface. Sand exposed exterior wood with 80 to 100 grit sandpaper to remove loose or weathered fibres. Attempt to remove existing stains by washing, sanding, scraping, etc. Spot prime knots and sap streaks with Zinsser® B-I-N Primer before priming full surface with Bulls Eye 1-2-3 Plus.

BRUKSANVISNING

Stir thoroughly before and while using. We only advise spot-priming for topcoats with high opacity. Ground the entire surface for maximum results. Keep the packaging sealed if the product is not used. Do not mix BE 123 Plus with any other paint for incompatibility reasons.

APPLICERINGSFÖRHÅLLANDEN

Air and surface temperature between 10°C and 25°C and relative humidity of less than 85%. The moisture level of the substrate may not exceed 12%.

APPLICERING OCH SPÅDNING: PENSEL

Use a nylon, polyester or synthetic brush. Do not dilute.

APPLICERING OCH SPÅDNING: ROLLER

Use a nylon, polyester or synthetic roller. Do not dilute.

APPLICERING OCH SPÅDNING: AIRLESSPRUTA

Spray opening: 0,017 inch..

Pressure: 140 -170 bar.

Do not dilute.

APPLICERING OCH SPÅDNING: TRYCKLUFTSSPRUTA

Pressure 3- 4 bar.

RENGÖRING AV UTRUSTNING/SPILL

Clean with liquid detergent and warm water. Use methylated spirits or appropriate solvent for dried spills or drips. If dried on tools, soak overnight in Mathys Brush Cleaner. Scrub bristles clean with a wire brush. Follow manufacturer's instructions when cleaning spray equipment.

ANMÄRKNINGAR

Bulls Eye 1-2-3 can be tinted towards top coat colour with up to 10ml universal colorant per 1L, improving the covering process by one layer.

Dry time: full bonding guaranteed after primer is totally cured (7 days).

Lower temperatures, high moisture substrate and addition of colorants will extend the dry time and cure time.

Limitations: Not recommended for application to floors or decks or to surfaces subject to immersion or prolonged contact with water. This list of limitations is not exhaustive.

Bulls Eye 1-2-3 Plus is guaranteed to perform as indicated when applied according to label directions to a properly prepared surface. Directions areas complete as possible but cannot encompass all conditions, applications, and / or surfaces beyond manufacturer's control.

Utgivet den: 04/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

ZINSSER® BULLS EYE 1-2-3 PLUS

SÄKERHETSDATA

VOC-nivå:	1.5 g/l
VOC färdigmix:	1.5 g/l
VOC-kategori:	A/g
VOC-gräns:	30 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from the production date in a closed can if it is stored in a dry, well ventilated area not exposed to direct sunlight and at temperatures between 5 and 35°C.

Utgivet den: 04/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu