



ZINSSER® WATERTITE

Low-odour, acrylic, waterproofing paint

- Stops up to 2,5 bar water pressure (twice the strength of latex waterproofers)
- Prevents water-seepage through cement, masonry and concrete block walls and basement floor
- Protection of the dried coat against fungal degradation
- Can be applied to wet or dry surfaces
- Smooth, non-yellowing eggshell finish

ZINSSER® WATERTITE

BESKRIVNING

Two coat system. The first coat primes and seals the surface. The second coat completes the sealing process to ensure protection against water intrusion and protection of the dried coat against fungal degradation.

REKOMMENDERAD ANVÄNDNING

For application on interior and exterior concrete, stucco, cement, cinder block and other masonry surfaces. Product is ideal for interior basement walls and for sealing concrete basement slabs prior to installing flooring (not recommended for foot traffic). Can also be applied on exterior foundations and retaining walls, above and below grade. Solvent based.

TEKNISK DATA

Densitet:	1,47
Glansnivå:	Matt
Torrsubstansvikt:	74%
Torrsubstansvolym:	48%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 h
Övermålningsbar:	4 h
Fultt hårdad:	7 - 14 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

400 - 500 µm per coat

REKOMMENDERAD TORRFILMSTJOCKLEK

220 - 260 µm per coat

TEORETISK FÖRBRUKNING

1,8 - 2,5 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

New or unpainted masonry: Surface must be clean and free of dirt, grease, oil, soap, and other contaminants. New masonry must cure at least 30 days before applying waterproofer. Salting or efflorescence (a white powdery deposit often found on walls) must be removed ("etched") with a solution of hydrochloric acid or concrete etching compound. Follow manufacturer's directions and safety precautions. Rinse the surface thoroughly with water after application.

Remove all existing mold and mildew. Use a solution of 1 teacup household bleach per litre water or use a mildew cleaner. For commercial buildings, follow appropriate guidelines for mould removal (if there is concern about mould and mildew behind walls, underneath flooring, in ventilation systems or other unseen areas, contact a professional who specializes in mould and mildew remediation. Remove exterior mould and mildew.

Previously painted surfaces: WATERTITE is guaranteed to produce a waterproof finish when applied to bare masonry. It can be used over previously painted, non-glossy surfaces, however its waterproofing ability is then dependent upon the integrity of the previous coating. For best results, remove as much of the old coating as possible by manually scraping the surface, followed by thorough wire brushing. A belt power sander with a 50 grit-sanding belt is also effective. Exterior surfaces should be cleaned by using high pressure (steam) cleaning or grit blasting to remove all loose and scaling paint and cement. Clean all surfaces with a solution of hydrochloric acid wash and rinse the surface thoroughly with water. Loose sand and grit caused by acid etching must be removed from the surface by vacuuming or sweeping.

Patching Water Leaks and Cracks: all holes & cracks, especially active water leaks, must be

patched with hydraulic cement. Seal the joint where the floor and wall meet with hydraulic cement. Follow manufacturer's directions for dry time, etc.

BRUKSANVISNING

Stir thoroughly before and during application.

APPLICERINGSFÖRHÄLLANDE

Temperature of air, substrate and coating material 10°C or higher. To ensure against accumulation of solvent vapours, be sure to open all windows and doors. Use a non-sparking exhaust fan to provide air movement. Extinguish all flames and pilot lights at water heaters and heating systems. Turn off air/heating systems at thermostat.

APPLICERING OCH SPÄDNING: PENSEL

Liberally apply the first coat using a thick polyester bristle brush, or by rolling a small section (1m x 1m), and then using a brush to work the coating into the pores of the masonry. Apply as much paint as necessary to produce a continuous, pinhole free film.

APPLICERING OCH SPÄDNING: ROLLER

Use a 24 mm nap roller for unpainted, porous surfaces, and an 18 mm nap roller for smooth or previously painted surfaces. The second coat can be brushed or rolled

RENGÖRING AV UTRUSTNING/SPILL

Wipe up fresh spills and drips with a rag and paint thinner. To minimize solvent odors, use odorless mineral spirits and clean application tools outside of the work area.

ANMÄRKNINGAR

- WATERTITE is not recommended for potable water tanks, cisterns, bird baths or swimming pools, or as a primer or finish on floors subject to foot traffic.
- Do not apply if heavy rain is expected within 24 hours.

SÄKERHETSDATA

VOC-nivå:	370 g/l
VOC färdigmix:	370 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 4 and 32°C.

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shandon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zellem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu